

Technical data sheet

Quality management ISO 9001:2015
Code TDEFa001
Revision 01

EGGER Flooring NatureSense Aqua

Coreboard	HDF+ (E1, CARB2/TSCA VI)
Profile	Aqua CLIC it!

Declared performance according to EN 14041

Formaldehyde according to EN 717-1	E1	Slip resistance according to EN 13893	DS ≥ 0,3
Thermal conductivity according to EN 12667	0,13 W/(m*K)	Fire classification according to EN 13501-1	Cfl-s1

Classification and general requirements according to EN 13329

Class of use	32	33
Guarantee domestic area	20 years	25 years
Guarantee comercial area	5 years	5 years
Abrasion resistance, test methode A according ISO 24338	AC4 / ≥ 4.000 cycles	AC5 / ≥ 6.000 cycles
Impact resistance, test methods "small/ big ball" according EN 17368 / EN13329, Annex C	≥ 35 mm ≥ 600 mm	≥ 70 mm ≥ 750 mm
Resistance to staining EN 438 - 2	group 1 + 2: level 5 group 3: level 4	group 1 + 2: level 5 group 3: level 4
Thickness swelling according ISO 24336	≤ 18 %	≤ 15 %
Static indentation by constant pressure according ISO 24343-1	≤ 0,05 mm	≤ 0,05 mm
Effect of furniture leg according EN ISO 16581 (foot Type 0)	No change in appearance or damage	No change in appearance or damage
Effect of a castor chair according EN ISO 4918	15.000 cycles	20.000 cycles
Profile strength lengthways / crossways according to ISO 24334	≥ 1,0 kN/m / ≥ 2,0 kN/m	≥ 1,0 kN/m / ≥ 2,0 kN/m
24h Water resistance according to ISO 4760	Qualitative rating after re-drying < 3 Quantitative rating after re-drying ≤ 0.3 mm, No water leakage	Qualitative rating after re-drying < 3 Quantitative rating after re-drying ≤ 0.3 mm, No water leakage
Dimensional tolerances of the board according to EN 17539	length ± 0,5 mm width ± 0,1 mm thickness ± 0,5 mm	length ± 0,5 mm width ± 0,1 mm thickness ± 0,5 mm

Format & Packaging

Dimension mm (length x width)	Medium	Classic	Classic	Large	Kingsize	Long	
	1.292 x 135	1.292 x 193	1.292 x 193	1.292 x 246	1.292 x 327	2050 x 246	
Total thickness	8mm	8 mm	10 mm	8 mm	8 mm	10mm	
Class of use 31							
Class of use 32	✓	✓	✓	✓	✓	✓	
Class of use 33		✓	✓				
Bevel, without							
Bevel, Lengthwise							
Bevel, circumferential	✓	✓	✓	✓		✓	
Bevel, circumferential + 1					✓		
Packet information (brutto)	Piece	8	8	7	8	6	5
	m ²	1,40	1,99	1,75	2,54	2,53	2,52
	kg (+/- 5%)	10,59	15,07	16,48	19,40	19,33	23,94
Pallet information	Packet per pallet	75	60	52	45	40	33
	m ²	104,65	119,69	90,77	114,42	101,40	83,21
	kg (+/- 5%)	802	912	865	881	781	798

Please find additional information on the backside



General information

Careful inspection of incoming materials is an essential part of any business transaction. Handling and storage of the flooring must be done with care. The flooring packages must be stored on level and dry ground, protected from weather in a closed building. We recommend conditioning the end products for at least 48 hours before installation according to the expected room climate ($> 18^{\circ}\text{C}$, 40 - 70 % relative humidity). Acclimatising takes place packed, lying flat with a minimum distance of 50 cm to all walls. Before and during installation, the floor elements must be checked for possible defects. Damaged flooring boards or those that differ from the norm should not be installed but returned to the supplier to be replaced. For more information, please visit www.egger.com

Environment and Health

The product has Type I, Type II and Type III eco-labels:

- EPD (Environmental Product Declaration) including externally verified life cycle assessment according to EN 15804
- environmental supplier declaration (Environmental and Health Datasheet)
- Blauer Engel, Greenguard, M1
- further information on the circular economy and sustainability can be found at www.egger.com/ecofacts.






EGGER laminate flooring consists of 83% renewable raw materials. The raw material wood absorbs CO₂ during its growth and stores it. CO₂ is emitted during transport and processing. The difference between the storage and the emission results in a CO₂ footprint.

Colour matching and surface texture

As slight colour variations occur due to inherent variations in the substrate, we recommend that components used next to each other – in one flooring surface – are selected from the same production batch to ensure colour uniformity or colour consistency.

Suitability for underfloor heating

EGGER floors are suitable for hot water underfloor heating and electric underfloor heating. The surface temperature of the heated flooring structure must not exceed 28° C and heating up too quickly must be avoided. Installation on surface heating systems with night storage function is not permitted. EGGER laminate floors may only be installed on electric flat / foil heating systems that are equipped with temperature sensors and controllers.

R - Thermal resistance according to EN 12667, $R_{\text{total}} = R_{\text{LF}} + R_{\text{S}}$ [(m ² *K)/W]			
Total thickness		8mm	10mm
R _{LF} Laminate Flooring		0,06	0,07
R _S Silenzio easy		0,057	
R _S Silenzio easy SD		0,057	
R _S Silenzio Professional SD		0,010	
R _S Silenzio Duo		0,040	

Accessories

When installing the floor, we recommend EGGER's own range of accessories with the product groups: EGGER Silenzio underlay mats, the matching MDF skirting boards, as well as many other accessories that are perfectly colour-coordinated with the flooring range on offer. You will find further information at www.egger.com.

A note on validity

This technical data sheet has been carefully drawn up to the best of our knowledge. It is intended for information only and does not constitute a guarantee in terms of product properties or suitability for specific applications. We accept no liability for any mistakes, errors in standards, or printing errors. In addition, technical changes may result from the further development of EGGER flooring as well as changes to standards and public law documents. This technical data sheet is not an instruction for use and is not a legally binding document.